

How does Tekton compare	Tekton	Barricade	FR1	Fastwrap	WaterGate Plus
Absorbent	No	No	Yes	Yes	Yes
Fire Rated (lower the better)	Yes, 0	No	Yes, 1	Yes, 4	Yes, 3
Tensile Strength Cross Direction (higher the better).	3.9kN	1.91kN	3.47kN	1.95kN	1.78kN
Tensile Strength Machine Direction (higher the better).	4.4kN	2.37kN	3.53kN	3.4kN	2.09kN
Edge Tear Machine Direction (higher the better).	228N	118.6N	160N	164N	110N
Edge Tear Cross Direction (higher the better).	186N	93.6N	155N	97N	91N
UV Stability	60 Days	42 days	42 days	42 days	60 days
Print Colour Options (higher the better).	33 Colour Palette	4	4	1	1

Note: There are no flexible wall underlays that permit internal wall / ceiling linings to be installed prior to the completion of the external cladding.